

# GREASE PREMUS MLB



#### **DESCRIPTION**

PREMUS MLB is a lithium-thickened lubricating grease enhanced with carefully selected and balanced package of additives and solid fillers including molybdenum disulfide (MoS<sub>2</sub>) to withstand high loads by forming a tenacious lubricating film on metal surfaces. It performs in a wide temperature range and wet and dusty operating environments. It is often used for the lubrication of inaccessible parts and where EP properties are required.

### **APPLICATIONS**

PREMUS MLB is suitable for the lubrication of wheel bearings, steering system bearings and all chassis points including ball joints and universal joints of both on-/off-highway equipment (i.e., trucks, tractors, cconstruction, mining and agricultural equipment). It can also be used in heavy-duty industrial and marine applications.

#### **CHARACTERISTICS-BENEFITS**

| CHARACTERISTICS   | BENEFITS   |  |
|---|--|--|
| Efficient lubrication to boundary friction conditions.  | Very effective anti-wear and EP protection.                |  |
| Outstanding film strength and adhesive properties.      | Protection against high and/or shock loads.                |  |
| Good water resistance.                                  | Long lasting rust and corrosion resistance.                |  |
| Stable and consistent under adverse service conditions. | Provides efficient protection over long service intervals. |  |

#### PHYSICAL-CHEMICAL CHARACTERISTICS

| CYCLON PREMUS MLB                                 | METHOD      |                       |
|---|-------------|-----------------------|
| NLGI  |             | 2                     |
| Color/Appearance                                  | Visual      | Black                 |
| Texture   | Visual      | Smooth                |
| Thickener type                                    |             | Lithium               |
| Base Oil  |             | Blend of mineral oils |
| Base oil viscosity @40°C, mm²/s                   | ASTM D445   | 200                   |
| Dropping point, °C                                | ASTM D2265  | 204                   |
| Worked penetration, mm/10 @25°C 60 strokes        | ASTM D 217  | 265-295               |
| EP properties weld point, kgf                     | ASTM D 2596 | 315                   |
| Wear preventive characteristics Scar diameter, mm | ASTM D 2266 | 0.5                   |
| Copper strip corrosion                            | ASTM D 4048 | 1b                    |
| Operating temperatures, °C                        |             | -25/+120              |

The abovementioned characteristics represent mean values.

## **SPECIFICATIONS**

